

**JLMJ CONSULTING**

NACE # 18375

"H2Poxy A" was applied on 12/26/2019 at an average of 13 mils DFT on a 4"x6", 1/16" thick metal coupon.

On December 30<sup>th</sup>, 2019 the coupon was weighed at 493.81 grams and submerged in saltwater at 1130 hours in 65-degree water.

On February 27<sup>th</sup>, 2020 at 1630 hours, the metal coupon was removed from the water, dried off, and weighed again.

After sitting in salt water for 59 days, the metal coupon weighed 493.81 grams.

The conclusion of this test is that "H2Poxy A" has proven to be hydrophobic.

John Leroy Mack Jr.

NACE # 18375

A handwritten signature in black ink, appearing to read "John Leroy Mack Jr.", written in a cursive style.